

Hi! I am ALLISON

LET'S KEEP IN TOUCH :-)



ALLISON weight

g/m²

ALLISON 5mm in kg/m ²	833
ALLISON 10mm in kg/m ²	1121
ALLISON 16mm in kg/m ²	1430

ALLISON bending stiffness*

Nm

ALLISON 5mm LG	19
ALLISON 5mm SG	9
ALLISON 10mm LG	81
ALLISON 10mm SG	37
ALLISON 16mm LG	229
ALLISON 16mm SG	96

*ISO5628

ALLISON FCT*

kPa, kN/m²

ALLISON 5mm	690
ALLISON 10mm	666
ALLISON 16mm	764

*DIN EN 23035

ALLISON ECT*

kN/m

ALLISON 5mm	8,8
ALLISON 10mm	10,3
ALLISON 16mm	10,8

*DIN EN ISO 3037

ALLISON PET*

J

ALLISON 5mm	10,6
ALLISON 10mm	
ALLISON 16mm	

*DIN 53142-1

ALLISON CIELAB colour*

L*a*b*

ALLISON 5, 10 & 16mm	95,8/0,6/-1,0
----------------------	---------------

*ISO 5631-1

ALLISON brightness*

%

ALLISON 5, 10 & 16mm	91
----------------------	----

*ISO 2470-1

ALLISON smoothness*

µm

ALLISON 5, 10 & 16mm	1,0
----------------------	-----

*ISO 8791-4

ALLISON gloss*

%

ALLISON 5, 10 & 16mm	48
----------------------	----

*Hunter 75°