

NFX20 Series Graphic Transparent UV Screen Ink

NFX20 Graphic Transparent Inks are designed to be vibrant in color and highly transparent, making them a great choice for printing on clear substrates, holographic substrates or metallic inks.

Substrates

Styrene (PS)
Rigid vinyl (PVC)
Polycarbonate (PC)
Coated paper / Coated cardstock
Pressure sensitive calendered vinyl (PVC)

Substrate Material(s) listed below may be Limited in Adhesion (*testing highly recommended for each print run*)
Acrylics (PMMA)

Substrate recommendations are based on commonly available materials intended for the ink's specific market when the inks are processed according to this technical data. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Reference the 'Quality Statement' at the end of this document.

Mesh

355tpi (140 tpcm) monofilament polyester mesh with a mesh opening of 22um for most applications.

Stencil

Use direct emulsions and capillary films which are solvent resistant and UV compatible.

Squeegee

70-90 durometer polyurethane squeegee.

Coverage

Depending upon ink deposit, the estimated coverage per gallon: 3,200 – 4,200 square feet (295 - 390 square meters)
Reference www.nazdar.com/en-us/ColorStar for examples of coverage calculations.

Screen Printing

Standard items are formulated to be press ready. Thoroughly mix the ink prior to printing. Improper mixing can lead to inconsistent color and ink performance.

Maintain ink temperature at 65°-90°F (18°-32°C) for optimum print and cure performance. Lower temperatures increase the ink viscosity, impairing flow and increasing film thickness. Elevated temperatures lower the ink viscosity, reducing print definition and film thickness.

Pretest to determine optimum printing parameters for a particular set of ink, substrate, screen, press, and curing variables/conditions.

The ink can be affected by stray UV light. Be aware of skylights, windows and overhead lights curing the ink in the screen; light filters are recommended. Leaving a container uncovered may result in the ink's surface forming a "skin", caused by reaction with ambient lighting. Keep containers covered.

Nazdar does not recommend inter-mixing this ink series with other inks or series.

Cure Parameters

These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions. "Undercuring" the ink may result in poor adhesion, lower block resistance, reduced durability, and higher residual odor. "Overcuring" the ink may reduce the flexibility of the printed part and adhesion of subsequent ink layers.

Mercury Vapor UV Curing: this series has been optimized for 395nm LED curing; however, most colors cure when exposed to a single medium pressure mercury vapor lamp emitting output millijoules (mJ) and milliwatts (mW) of:
130-200 mJ/cm² @ 600+ mW/cm² UVA for most colors

To increase mJ levels, slow down the belt speed or scan speed. To increase mW levels, increase the wattage setting of the UV

NFX20 Series Graphic Transparent UV Screen Ink

reactor. To optimize mJ and mW output, maintain the bulb and reflector, and ensure proper focus to the substrate. These guidelines are representative of measurements taken using an EIT® UVICURE® Plus radiometer measuring the UVA bandwidth (320-390 nm). To obtain accurate mJ readings with the UVICURE® Plus, reduce the belt speed to less than 40 ft/min.

Processing

Background Color: Due to the high transparency of the inks, the background color will have significant effect on color.

Inter-Printable

It is recommended to use only an overprint on the substrates outlined in the 'Substrate' section. These inks can be inter-printed with the following ink series.

Nazdar 1600 UV Ink Series
Nazdar 1800 UV Ink Series
Nazdar 1900 UV Ink Series
Nazdar 4200 UV Ink Series
Nazdar 4000 UV Ink Series

Refer to the inter-printed ink's Technical Data Sheet for processing recommendations.

Adhesion Testing

When recommended UV energy output levels are achieved, checking the degree of cure on a **cooled down** print is imperative:

- Touch of ink surface – the ink surface should be smooth.
- Thumb twist – the ink surface should not mar or smudge.
- Scratch surface – the ink surface should resist scratching.
- Cross hatch tape test – per the ASTM D-3359 method, use a cross hatch tool or a sharp knife to cut through ink film only; then apply 3M #600 clear tape on cut area, rub down, and rip off at a 180 degree angle. Ink should only come off in actual cut areas.

Full adhesion characteristics at proper cure levels are demonstrated within: 8 hours

Cleanup

For screen cleaning, similar products to those listed below may be used.

Screen Wash (Prior to Reclaim): Use IMS201 Premium Graphic Screen Wash or IMS203 Economy Graphic Screen Wash
Press Wash (On Press): Use IMS301 Premium Graphic Press Wash

Ink Modifications

Clears / Varnishes

Mixing Clear: use to reduce the density of colors.

Additives

The market specific performance properties of this ink series / ink item should be acceptable for most applications without the need for additives. When required, any additives should be thoroughly mixed before each use. Prior to production, test any additive adjustment to the ink. Inks containing additives should not be mixed with other inks.

Prior to production, test any additive adjustment to the ink. Inks containing additives should not be mixed with other inks.

Example for additives: Ink at 100g with 8% of an additive is calculated as: 100g ink + 8g additive = 108g total

Reducer / Thinner

Use the following item(s) to reduce the viscosity of these inks. Over reduction can reduce print definition, film thickness and adversely affect cure.

RE310 UV Reducer: add up to 5%

Flexibilizer

Use the following item(s) to increase the flexibility of these inks. The addition of flexibilizer could show a decrease in block resistance.

RE308 UV Reducer: add up to: 10%

NFX20 Series Graphic Transparent UV Screen Ink

Adhesion Promoter

Use the following item(s) to enhance adhesion.

NB80 UV Adhesion Promoter: add up to: 5%. Improved adhesion will be demonstrated within 8-24 hours, with full crosslinking in 4-7 days. Ink mixed with NB80 UV Adhesion Promoter has a 4-8 hour pot life. NB80 is sensitive to humidity and moisture; clean the lid and container thoroughly after each use to prevent fusing of the container.

General Information

Handling

Refer to the SDS for recommendations on handling.

Wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If product does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water.

Consult the applicable Safety Data Sheet (SDS / MSDS) for further instructions and warnings.

For assistance on a wide range of important regulatory issues, consult the following Regulatory Compliance Department link at <http://www.nazdar.com> or contact Nazdar Ink Technologies - World Headquarters (see contact listing at the end of this document).

This ink series is a one-part, 100% solids UV-curable screen printing ink and does not contain N-vinyl-2-pyrrolidone (trade name V-Pyrol®).

Storage / Shelf Life

Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life.

Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink. Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life.

Standard items supplied in 1-gallon (4/5 kilo) containers or smaller. Useable for a period of at least **24 months** from the date of manufacture.

Shelf life above applies to the standard ink items listed on this TDS. To obtain the shelf life for special inks and additives, contact Nazdar Customer Service or Nazdar Technical Service. See contact listing at the end of this document.

Standard Color Range

Based on information from our raw material suppliers, these ink products are formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

Packaging / Availability

Contact your Nazdar distributor for product availability and offering.

Item Type	Item Number	Item (or Color) Description
Standard Colors	NFX21	Graphic Transparent Clear
Standard Colors	NFX22	Graphic Transparent Red
Standard Colors	NFX23	Graphic Transparent Magenta
Standard Colors	NFX24	Graphic Transparent Violet
Standard Colors	NFX25	Graphic Transparent Blue
Standard Colors	NFX26	Graphic Transparent Green
Standard Colors	NFX27	Graphic Transparent Yellow
Standard Colors	NFX29	Graphic Transparent Black
Additives	NB80	UV Adhesion Promoter
Additives	RE308	UV Reducer
Additives	RE310	UV Reducer

NFX20 Series Graphic Transparent UV Screen Ink

Cleaners	IMS201	Premium Graphic Screen Wash
Cleaners	IMS203	Economy Graphic Screen Wash
Cleaners	IMS301	Premium Graphic Press Wash

Nazdar Quality Statement

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

**Nazdar Ink Technologies
Offices**

Nazdar Ink Technologies - World Headquarters
8501 Hedge Lane Terrace
Shawnee, KS 66227-3290 USA
Toll Free US: 866-340-3579
Tel: +1 913-422-2255
Fax: +1 913-422-2296
Customer Service E-mail: NazdarOrders@nazdar.com
Technical Support E-mail: TechSupport@Nazdar.com

Nazdar Limited – EMEA
Battersea Road, Heaton Mersey
Stockport, England SK4 3EA
Tel: + 44 (0)-161-442-2111
Fax: + 44 (0)-161-442-2001
EMEA Customer Service E-mail: infoUK@nazdar.com
EMEA Technical Service E-mail: technicalservicesUK@nazdar.com

Nazdar – Asia Pacific
11 Changi North Street 1
#03-03/04
Singapore 498823
Tel: +65 6385 4611
E-mail: aspac@nazdar.com