







Overview

Main Benefits

- Tested and approved for digital
- Bright white, smooth and uniform surface
- Available in a wide range of standard and special designer colors
- Standard matte or gloss finishes
- Good insulation, lower heat transmission
- Non-toxic
- Good flammability: self extinguishing
- Half the weight of solid PVC sheets
- Same thickness at lower cost
- Good mechanical properties
- Easily worked with conventional tools, prints and paints
- Can be easily bonded, nailed and bolted
- Low water absorption
- High chemical resistance
- Meet various international standards

Typical Applications

Advertising

Signs, displays, interior decoration, exhibition graphics, cladding etc.

Construction

Models, partitions, wall cladding, interior decoration, air conditioning ducts, etc...

Industry

Control cabinets and panels, structures for corrosive environments, ducts, etc.

Serigraphy (Screen Printing)

PALIGHT's flat, consistent surface makes it ideal for screen printing. It is suitable for use with aqueous and solvent-based inks. PALIGHT's sheet surface has low absorption giving excellent ink yield.

Digital Printing

PALIGHT was approved by major digital flatbed printer manufacturers, and is suitable for use with digital inks and UV curing. All 1-10mm white PALIGHT sheets have a bright and smooth surface for true color interpretation.

www.palram.com



Standard Dimensions*

| | Color | | Thickness Availability / Dimensions (mm) | | | |
|----------|--------|--------|--|-----------|----------------|--|
| PALIGHT® | | | 1220x2440 | 1560x3050 | 2030x3050 | |
| | White | ST-10 | 1-13, 15, 19 24, 25, 30, 40 | All | All | |
| | Yellow | ST-30 | 3, 5 | | | |
| | Red | ST-50 | 3, 5 | | 3, 5 | |
| | Black | ST-90 | 3, 5, 10 | 3, 5 | 3, 5, 6, 8, 10 | |
| | Blue | ST-70 | 3, 5 | | 3, 5 | |
| | Green | ST-80 | 3 | | | |
| | Grey | ST-100 | 3, 5 | 3,5 | 3, 5 | |

^{*} Special dimensions are available upon request.

Product Range

| Product | Description |
|----------------|---|
| PALIGHT® | Flat foamed PVC sheet with matte finish, available in a wide range of standard and special thicknesses and designer colors. |
| PALFOAM™ | Cost-effective, white only, light weight flat foamed PVC sheet. |
| PALIGHT® Print | Flat foamed PVC sheet made specifically to cost effectively meet the stringent requirements of large format print imaging industry. |
| PALFOAM™ LW | Low weight, white only, flat foamed PVC sheet for general purposes. |

Typical Physical Properties

| Property | ASTM Method | Conditions | Units | Value |
|-----------------------------|----------------------|----------------|----------|----------------------|
| Density | (D-792) | | g/cm³ | 0.57* |
| Water Absorption | (D-570) | 24 hr. @ 23 °C | % | 0.5-0.8** |
| Flexural Strength at Yield | (D-790) | 1mm/min. | MPa | 28* |
| VICAT Softening Temp | (D-1525) | Load: 1kg | °C | 75 |
| Coefficient of Linear Therm | al Expansion (D-696) | | cm/cm °C | 6.7x10 ⁻⁵ |
| Thermal Conductivity | (C-177) | | W/mK | 0.06-0.07** |
| Surface Resistance | (D-257) | | Ohm | 5X10 ¹⁵ |
| Volume Resistance | (D-257) | | Ohm-cm | 2X10 ¹⁶ |
| | | | | |

^{*}Results refer to 3mm sheet **Depending on thickness (3-10mm)

Flammability

PALIGHT is self extinguishing and complies with the most demanding international fire resistance standards defined in the field of plastics, as indicated by representative results in the attached table.

| Standard | Classification* |
|-------------|-----------------|
| EN 13501 | B, s1-3, d0 |
| BS 476/7 | Class 1 |
| NSP 92501,5 | M-1, M-2 |
| UL 94 | V-0 |
| | |

^{*}Depends on thickness, type and color.

Color Chart

| Standard Colors | Code | PANTONE® | RAL |
|-----------------|--------|----------|------|
| White* | ST-10 | | |
| Red | ST-50 | 1807U | - |
| Yellow | ST-30 | 108U | - |
| Blue | ST-70 | 288C | - |
| Green | ST-80 | 3415C | - |
| Black | ST-90 | 4C | 9011 |
| Grey | ST-100 | 430C | 7037 |

^{*} Whites are divided by thickness: 1-10mm: ST-10 12-25mm: Classic White

| Designer Colors | Code | PANTONE® | RAL |
|-----------------|--------|--------------|------|
| Digital White | DE-11 | | |
| Cream | ST-20 | - | 9001 |
| Antique Cream | DE-21 | Warm Grey 2C | 1013 |
| Smoke Grey | DE-141 | 428C | 7047 |
| Dim Grey | DE-151 | 408C | = |
| Dark Grey | DE-131 | 431C | 7012 |
| Burgundy | DE-71 | 187C | 3002 |
| Cardinal Red | DE-211 | 193C | 3031 |
| Firebrick Red | DE-61 | 485C | = |
| Orchid Pink | DE-221 | 204C | 4003 |
| Orange | DE-51 | 21C | 2004 |
| Blaze Orange | DE-41 | 158C | 2011 |
| Bright Yellow | ST-40 | 1235C | - |
| Lemon | DE-31 | 102C | - |
| Lime green | DE-181 | 390C | - |
| Sea Green | DE-171 | 361C | 6018 |
| Mint Green | DE-111 | 340C | 6024 |
| Olive Green | DE-161 | 378C | - |
| Dark Green | DE-121 | 3308C | 6005 |
| Turquoise | DE-101 | 337C | - |
| Steel Blue | DE-81 | 2707C | = |
| Sky Blue | DE-201 | 7401C | - |
| Light Blue | ST-60 | 2935C | - |
| Royal Blue | DE-191 | 287C | - |
| Sapphire Blue | DE-91 | 2757C | 5002 |
| | | | |



PALRAM H.Q.

Tel: +972 4 8459900 Fax: +972 4 8444012 palram@palram.com

PALRAM EUROPE LTD.

Tel: +44 1302 380777 Fax: +44 1302 380778 sales.europe@palram.com

PALRAM AMERICAS

Tel: 610 2859918 Fax: 610 2859928 palramamericas@palram.com



17

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.











