

PVC - Free

Mediatex® ART-TEX SE

Spezifikation (Specification)	Einheit (unit)	Norm (standard)	Wert (value)
Substrat : (substrate)		(DIN 60001)	100% BW 100% cotton
Flächengewicht: (weight)	[g/m ²]	(DIN EN ISO 2286-2)	370 ±20
Materialdicke (thickness)	[mm]	(DIN EN ISO 2286-3)	0,60± 0,05
Reißkraft K/S (tensile strength warp/weft)	[daN/5cm]	(DIN 53857 T1)	> 70/55
Weiterreißkraft K/S (tear resistance warp/weft)	[N]	(DIN 53857 T2)	> 15/12
Weißgrad (whiteness)		(nach Berger)	85- 100
Lichtechtheit (light fastness)	[Note] [grade]	(DIN EN ISO 105-B02)	≥ 6
Schwerentflammbarkeit: (flame retardant)		DIN 4102 B1	ja yes
Tintentyp (type of ink)			wässrige Pigment-Tinten waterbased pigment ink
Anwendung (use)			innen indoor
Breite : (width)	[cm] [inch]	(DIN EN ISO 2286-1)	max. Breite: 152,4 max. width: 60
Druckseite: (prints side)			außen outside
Rollenlänge (length of the roll)		(-)	15 ± 0,5

The article Mediatex® Art-Tex SE is onesided triple coated with a special polymercoating which allows a high whiteness. Additionally you get a highly brilliant print at a maximum of dyestuff yield.

Mediatex® Art-Tex SE is the only genuine canvas for art reproductions, which is flame resistant as 100% natural fiber. Mediatex® Art-Tex SE delivers the best print results with 3K inks from Epson.

Mediatex® Art-Tex SE has been tested with the following printers:

HP 5500 • Epson •
Canon • etc.

Please see for yourself at a test.



All details are nominal values and are subject to change within usual tolerances (±5%).

The information provided in this document is based on current knowledge and experience. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor.

date: 11/2010